QC - Concrete Cube Testing Report.

Company: MRMA(LLP)

Project: GMR

Report for Month: Feb - Mar = 2022.

Prepared By: QC Team

Date: 04-04-2022.

S. No.	Date of casting	Site Mix or RMC	Specified Grade of Concrete	Supplier / Contractor	D. C. No	Block No. / Bungalow No.	Used for Slab / Columns	Slab No. or Column No.	Date of Testing	No. of days	Specified Strength	Tested Strength Kilo-newtons	Tested Strength in N per sq. mm	Avg. of three tests	Remarks
16176	12-02-2022	RMC	M20	SSVC		C.B.	Slab	6	20-2-22	8	14.0	325.0	14.4		
											14.0	335.0	14.9	14.6	
											14.0	325.0	14.4		
16176	12-02-2022	RMC	M20	SSVC		C.B.	Slab	6	14-3-22	30	20.0	450.0	20.0		
											20.0	465.0	20.7	20.7	
											20.0	480.0	21.3		
16177	14-02-2022	Site Mix	M25	SCPL		H-block	)L(001 - 0(	1	20-2-22	6	17.5	395.0	17.6		
											17.5	405.0	18.0	17.6	
											17.5	390.0	17.3		
16177	14-02-2022	Site Mix	M25	SCPL		H-block	)L(001 - 0(	1	14-3-22	28	25.0	575.0	25.6		
											25.0	585.0	26.0	25.9	
											25.0	585.0	26.0		
16178	21-02-2022	RMC	M20	SCPL		H-block	ab(001-00	1	28-2-22	7	14.0	330.0	14.7		
											14.0	335.0	14.9	14.7	
											14.0	330.0	14.7		
16178	21-02-2022	RMC	M20	SCPL		H-block	ab(001-00	1	23-3-22	30	20.0	455.0	20.2		
											20.0	470.0	20.9	20.7	
											20.0	475.0	21.1		
16179	23-02-2022	RMC	M20	Pointech		H-block	ab(005 -00	1	3-3-22	8	14.0	315.0	14.0		
											14.0	330.0	14.7	14.4	
											14.0	325.0	14.4		
16179	23-02-2022	RMC	M20	Pointech		H-block	ab(005 -00	1	26-3-22	31	20.0	455.0	20.2		
											20.0	465.0	20.7	20.5	
											20.0	465.0	20.7		
16180	03-03-2022	RMC	M20	Bikshapathi		C-block	ab(601 -60	8	12-3-22	9	14.0	335.0	14.9		
											14.0	330.0	14.7	14.9	
											14.0	340.0	15.1		
16180	03-03-2022	RMC	M20	Bikshapathi		C-block	ab(601 -60	8	1-4-22	29	20.0	460.0	20.4		
											20.0	470.0	20.9	20.8	
											20.0	475.0	21.1		