

S. No.	Date of casting	Site Mixor RMC	Specified Grade of Concrete	Supplier / Contractor	D. C.No	Block No./ Baugataw No.	Used for Slab / Columns	Slab No. or Column No.	Date of Testing	No. of days	Specified Strength	Tested Strength Kilo-newtons	Tested Strength in N per sq. mm	Avg. of three tests	Remarks
16181	11-05-2022	RMC	M20	CemexInfra		H-block	Slab	2	19-5-22	8	14.0	325.0	14.4		
											14.0	340.0	15.1	14.7	
											14.0	325.0	14.4		