QC - Concrete Cube Testing Report.

Company: MRP(LLP)

Project: NGH

Report for Month: Aug - Sep= 2022.

Prepared By: QC Team

Date: 04-10-2022

S. No.	Date of casting	Site Mix or RMC	Specified Grade of Concrete	Supplier / Contractor	D. C. No	Block No. / Bungalow No.	Used for Slab / Columns	Slab No. or Column No.	Date of Testing	No. of days	Specified Strength	Tested Strength Kilo-newtons	Tested Strength in N per sq. mm	Avg. of three tests	Remarks
22153	01-08-2022	Site Mix	M30	Svc		A(S.T.)	COL	5	10-8-22	9	21.5	495.0	22.0		
											21.5	480.0	21.3	21.7	
											21.5	490.0	21.8		
22153	01-08-2022	Site Mix	M30	Svc		A(S.T.)	COL	5	30-8-22	29	30.0	695.0	30.9		
											30.0	680.0	30.2	30.3	
											30.0	670.0	29.8		
22154	15-08-2022	RMC	M25	VR infra		A	Slab	5 (3 -5)	23-8-22	8	17.5	395.0	17.6		
											17.5	410.0	18.2	17.7	
											17.5	390.0	17.3		
22154	15-08-2022	RMC	M25	VR infra		A	Slab	5 (3 -5)	13-9-22	29	25.0	595.0	26.4		
											25.0	590.0	26.2	26.1	
											25.0	580.0	25.8		
22155	20-08-2022	Site Mix	M30	Svc		A	COL	6(5,6,7)	28-8-22	8	21.5	490.0	21.8		
											21.5	485.0	21.6	21.6	
											21.5	480.0	21.3		
22155	20-08-2022	Site Mix	M30	Svc		A	COL	6(5,6,7)	18-9-22	29	30.0	690.0	30.7		
											30.0	685.0	30.4	30.4	
											30.0	675.0	30.0		
22156	25-08-2022	RMC	M25	Cemex Infra		A	Slab	5 (1,2,9)	2-9-22	8	17.5	400.0	17.8		
											17.5	410.0	18.2	17.9	
											17.5	395.0	17.6		
22156	25-08-2022	RMC	M25	Cemex Infra		A	Slab	5 (1,2,9)	23-9-22	29	25.0	590.0	26.2		
											25.0	610.0	27.1	26.3	
											25.0	575.0	25.6		
22157	29-08-2022	Site Mix	M30	Svc		A	COL	6(2,3,8)	7-9-22	9	21.5	495.0	22.0		
											21.5	490.0	21.8	21.8	
											21.5	485.0	21.6		
22157	29-08-2022	Site Mix	M30	Svc		A	COL	6(2,3,8)	27-9-22	29	30.0	695.0	30.9		
											30.0	690.0	30.7	30.6	
											30.0	680.0	30.2		
22158	03-09-2022	Site Mix	M30	Svc		A	COL	6(1,9)	11-9-22	8	21.5	505.0	22.4		
											21.5	505.0	22.4	22.1	
											21.5	485.0	21.6		
22159	06-09-2022	RMC	M25	Cemex Infra		B	Footings	Footings	14-9-22	8	17.5	405.0	18.0		
											17.5	418.0	18.6	18.4	
											17.5	422.0	18.8		
22160	16-09-2022	RMC	M25	Cemex Infra		B	P.B.	P.B.	24-9-22	8	17.5	395.0	17.6		
											17.5	400.0	17.8	17.9	
											17.5	415.0	18.4		
22161	20-09-2022	RMC	M25	Cemex Infra		A	Slab	6(2 - 7)	28-9-22	8	17.5	420.0	18.7		
											17.5	420.0	18.7	18.6	
											17.5	418.0	18.6		

QC - Concrete Cube Testing Report.

Company: MRP(LLP)

Project: NGH

Report for Month: July - Aug = 2022.

Prepared By: QC Team

Date: 01-09-2022

S. No.	Date of casting	Site Mix or RMC	Specified Grade of Concrete	Supplier / Contractor	D. C. No	Block No. / Bungalow No.	Used for Slab / Columns	Slab No. or Column No.	Date of Testing	No. of days	Specified Strength	Tested Strength Kilo-newtons	Tested Strength in N per sq. mm	Avg. of three tests	Remarks
22150	16-07-2022	RMC	M25	VR infra		A	Slab	4	14-8-22	29	25.0	590.0	26.2		
											25.0	595.0	26.4	26.7	
											25.0	615.0	27.3		
22151	18-07-2022	Site Mix	M30	Svc		A	Columns	5	16-8-22	29	30.0	690.0	30.7		
											30.0	695.0	30.9	31.1	
											30.0	715.0	31.8		
22152	22-07-2022	Site Mix	M30	Svc		A	Columns	5	20-8-22	29	30.0	675.0	30.0		
											30.0	695.0	30.9	30.8	
											30.0	710.0	31.6		