

S. No.	Date of casting	Site Mix or RMC	Specified Grade of Concrete	Supplier / Contractor	D. C. No	Block No. / Bungalow No.	Used for Slab / Columns	Slab No. or Column No.	Date of Testing	No. of days	Specified Strength	Tested Strength Kilo-newtons	Tested Strength in N per sq. mm	Avg. of three tests	Remarks
18208	29-03-2022	Rmc	M20	Homeline	A-701,702,716		slab	9	7-4-22	9	14.0	335.0	14.9		
											14.0	335.0	14.9	14.7	
											14.0	320.0	14.2		
18208	29-03-2022	Rmc	M20	Homeline	A-701,702,716		slab	9	27-4-22	29	20.0	435.0	19.3		
											20.0	455.0	20.2	20.1	
											20.0	465.0	20.7		
18209	08-04-2022	Rmc	M20	Homeline	A-703-705,714		slab	9	16-4-22	8	14.0	340.0	15.1		
											14.0	340.0	15.1	14.9	
											14.0	325.0	14.4		
18209	08-04-2022	Rmc	M20	Homeline	A-703-705,714		slab	9	6-5-22	28	20.0	440.0	19.6		
											20.0	460.0	20.4	20.4	
											20.0	475.0	21.1		