

S. No.	Date of casting	Sin Mix or RMC	Specified Grade of Concrete	Supplier / Contractor	D.C.No	Block No. / Bungalow No.	Used for Slab / Columns	Slab No. or Column No.	Date of Testing	No. of days	Specified Strength	Tested Strength Kilo-newtons	Tested Strength in N per sq. mm	Avg. of three tests	Remarks
14207	28-11-2022	RMC	M25	SL Infra		4545	Slab	5	26-12-22	28	25.0 25.0 25.0	599.0 595.0 555.0	26.6 26.4 24.7	25.9	
14208	02-12-2022	RMC	M25	KN Infra		3600 A&C	Footings		10-12-22	8	17.5 17.5 17.5	415.0 393.0 425.0	18.4 17.5 18.9	18.3	