QC - Concrete Cube Testing Report.																
Company:		GVRC														
Project:		Innopolis														
Report for Month:		(Dec - Jan) = 2023 - 2024.														
Prepared By:		QC Team														
Date:		31-01-2024														

S. No.	Date of casting	Site Mix or RMC	Specified Grade of Concrete	Supplier / Contractor	D. C. No	Block No. / Bungalow No.	Used for Slab / Columns	Slab No. or Column No.	Date of Testing	No. of days	Specified Strength	Tested Strength Kilo-newtons	Tested Strength in N per sq. mm	Avg. of three tests	Remarks	
14222	05-12-2023	RMC	M25	R6 Infra		4545(D.W.	Slab	2	4-1-24	30	25.0	595.0	26.4			
											25.0	565.0	25.1	25.8		
											25.0	580.0	25.8			
14223	09-12-2023	RMC	M25	R6 Infra		3600	Slab	3	8-1-24	30	25.0	590.0	26.2			
											25.0	575.0	25.6	26.2		
											25.0	605.0	26.9			
14224	14-12-2023	RMC	M30	R6 Infra		3600	COL	4	13-1-24	30	30.0	694.0	30.8			
											30.0	698.0	31.0	30.8		
											30.0	690.0	30.7			
14225	30-12-2023	RMC	M30	R6 Infra		4500	footings		8-1-24	9	21.5	510.0	22.7			
											21.5	512.0	22.8	22.5		
											21.5	496.0	22.0			