

S. No.	Date of casting	Site Mix or RMC	Specified Grade of Concrete	Supplier / Contractor	D. C. No	Block No. / Bungalow No.	Used for Slab / Columns	Slab No. or Column No.	Date of Testing	No. of days	Specified Strength	Tested Strength Kilo-newtons	Tested Strength in N per sq. mm	Avg. of three tests	Remarks
18210	30-08-2022	Rmc	M20	Homeline		L.M.R.	slab	10	8-9-22	9	14.0 14.0 14.0	335.0 335.0 320.0	14.9 14.9 14.2	14.7	
18210	30-08-2022	Rmc	M20	Homeline		L.M.R.	slab	10	29-9-22	30	20.0 20.0 20.0	485.0 495.0 470.0	21.6 22.0 20.9	21.5	