

21/2

QC - Concrete Cube Testing Report															
Company	Super Builders														
Project	Nagar Heights II														
Report for Month	Dec-15														
Prepared By	S. Suresh Kumar														
Date	13-11-2015														
S. No.	Date of casting	Site Mix or RMC	Specified Grade of Concrete	Supplier / Contractor	D. C. No.	Block No. / Bungalow No.	Used for Slab / Column	Slab No. or Column No.	Date of Testing	No. of days	Specified Strength	Tested Strength Kilo-newtons	Tested Strength in N per sq. mm	Avg. of three tests	Remarks
5218	03-09-2015	Site Mix	M20	Amud		61	Slab-1		12-9-15	(9)	14.0	380.0	16.9	16.7	✓
											14.0	370.0	16.4		
											14.0	375.0	16.7		
5218	03-09-2015	Site Mix	M20	Amud		61	Slab-1		1-10-15	(28)	20.0	515.0	22.9	23.1	✓
											20.0	515.0	22.9	23.1	
											20.0	530.0	23.6		
5219	03-09-2015	Site Mix	M20	Amud		62	Slab-1		12-9-15	(9)	14.0	385.0	17.1		✓
											14.0	360.0	16.0	16.4	
											14.0	360.0	16.0		
5219	03-09-2015	Site Mix	M20	Amud		62	Slab-1		1-10-15	(28)	20.0	520.0	23.1	22.9	✓
											20.0	520.0	23.1		
											20.0	505.0	22.4		
5220	03-09-2015	Site Mix	M20	Amud		31	Pinch beam		12-9-15	(9)	14.0	373.0	16.7		✓
											14.0	375.0	16.7	16.8	
											14.0	385.0	17.1		
5220	03-09-2015	Site Mix	M20	Amud		31	Pinch beam		1-10-15	(28)	20.0	510.0	22.7		✓
											20.0	525.0	23.3	22.8	
											20.0	505.0	22.4		
5221	03-09-2015	Site Mix	M20	Amud		56	Pinch beam		12-9-15	(9)	14.0	370.0	16.4		✓
											14.0	375.0	16.7	16.5	
											14.0	365.0	17.6		
5221	03-09-2015	Site Mix	M20	Amud		58	Pinch beam		1-10-15	(28)	20.0	525.0	23.3	23.8	✓
											20.0	545.0	24.2	23.8	
											20.0	500.0	22.2		
5222	07-09-2015	Site Mix	M20	Amud		26	Footing		15-9-15	(8)	14.0	365.0	16.2		✓
											14.0	360.0	16.0	16.0	
											14.0	355.0	15.8		
5222	07-09-2015	Site Mix	M20	Amud		26	Footing		7-10-15	(30)	20.0	510.0	22.7	22.4	✓
											20.0	500.0	22.2	22.4	
											20.0	505.0	22.4		

5223	08-09-2015	Site Mix	M20	Amount	9	blunt beam	15-9-15	(7)	14.0	560.0	16.0	✓
									14.0	550.0	15.8	16.0
									14.0	365.0	16.2	
5223	08-09-2015	Site Mix	M20	Amount	9	blunt beam	7-10-15	(26)	20.0	500.0	22.2	✓
									20.0	435.0	22.0	22.3
									20.0	510.0	22.7	
5224	09-09-2015	Site Mix	M25	Amount	59	col-1	17-9-15	(8)	17.5	385.0	17.6	✓
									17.5	405.0	18.0	17.9
									17.5	410.0	18.2	
5224	09-09-2015	Site Mix	M25	Amount	59	col-1	7-10-15	(28)	25.0	565.0	25.1	✓
									25.0	560.0	24.9	24.7
									25.0	515.0	24.2	
5226	09-09-2015	Site Mix	M20	Amount	63	slab-1	17-9-15	(8)	14.0	315.0	16.7	✓
									14.0	380.0	16.9	16.8
									14.0	386.0	16.9	
5226	09-09-2015	Site Mix	M20	Amount	63	slab-1	7-10-15	(26)	20.0	505.0	22.4	✓
									20.0	515.0	22.9	22.9
									20.0	525.0	23.3	
5227	09-09-2015	Site Mix	M20	Amount	23	blunt beam	17-9-15	(8)	14.0	365.0	16.2	✓
									14.0	355.0	15.8	16.3
									14.0	380.0	16.9	
5227	08-09-2015	Site Mix	M20	Amount	23	blunt beam	7-10-15	(28)	20.0	525.0	23.3	✓
									20.0	530.0	23.6	23.2
									20.0	510.0	22.7	
5228	15-09-2015	Site Mix	M25	Amount	56	col-1	23-9-15	(8)	17.5	390.0	17.3	✓
									17.5	405.0	18.0	17.8
									17.5	405.0	18.0	
5228	15-09-2015	Site Mix	M25	Amount	56	col-1	14-10-15	(29)	25.0	535.0	25.4	✓
									25.0	580.0	25.8	26.1
									25.0	585.0	26.0	
5230	16-09-2015	Site Mix	M25	Amount	73	col-1	23-9-15	(7)	17.5	405.0	18.0	✓
									17.5	410.0	18.2	17.9
									17.5	390.0	17.3	
5230	16-09-2015	Site Mix	M25	Amount	73	col-1	14-10-15	(28)	25.0	530.0	26.2	✓
									25.0	535.0	26.5	26.3
									25.0	510.0	25.3	
5231	17-09-2015	Site Mix	M25	Amount	33	col-1	24-9-15	(7)	17.5	390.0	17.3	✓
									17.5	405.0	18.0	17.8
									17.5	405.0	18.0	
5231	17-09-2015	Site Mix	M25	Amount	33	col-1	15-10-15	(28)	25.0	585.0	26.0	✓
									25.0	590.0	26.2	26.0
									25.0	580.0	25.8	

5232	18-09-2015	Site Mix	M25	Amend		32	col.1	26-9-15	(8)	17.5	410.0	18.2	18.1	✓
										17.5	400.0	17.8	18.1	
										17.5	410.0	18.2		
5232	18-09-2015	Site Mix	M25	Amend		32	col.1	17-10-15	(29)	25.0	590.0	25.2	26.3	✓
										25.0	605.0	26.0		
										25.0	580.0	25.8		
5233	21-09-2015	Site Mix	M20	Amend		65	Sub-1	29-9-15	(8)	14.0	365.0	16.2		✓
										14.0	370.0	16.4	16.5	
										14.0	385.0	17.1		
5233	21-09-2015	Site Mix	M20	Amend		65	Sub-1	19-10-15	(28)	20.0	525.0	23.3	23.8	✓
										20.0	535.0	23.8		
										20.0	545.0	24.2		
5234	22-09-2015	Site Mix	M20	Amend		24	Sub-1	29-9-15	(7)	14.0	365.0	16.2		✓
										14.0	360.0	16.0	16.0	
										14.0	355.0	15.8		
5234	22-09-2015	Site Mix	M20	Amend		24	Sub-1	19-10-15	(41)	20.0	505.0	22.4		✓
										20.0	525.0	23.3	23.2	
										20.0	535.0	23.8		
5235	23-09-2015	Site Mix	M25	Amend		65	col.2	30-9-15	(7)	17.5	385.0	17.1		✓
										17.5	410.0	18.2	17.9	
										17.5	415.0	18.4		
5235	23-09-2015	Site Mix	M25	Amend		65	col.2	22-10-15	(29)	25.0	595.0	26.4	26.2	✓
										25.0	595.0	26.4		
										25.0	580.0	25.8		
5236	23-09-2015	Site Mix	M25	Amend		65	col.2	1-10-15	(8)	17.5	395.0	17.6		✓
										17.5	390.0	17.3	17.5	
										17.5	385.0	17.6		
5236	23-09-2015	Site Mix	M25	Amend		65	col.2	22-10-15	(29)	25.0	565.0	25.1		✓
										25.0	560.0	24.9	25.4	
										25.0	590.0	26.2		
5237	24-09-2015	Site Mix	M25	Amend		62	col.2	1-10-15	(7)	17.5	405.0	18.0		✓
										17.5	415.0	18.4	18.3	
										17.5	415.0	19.4		
5238	24-09-2015	Site Mix	M25	Amend		62	col.2	22-10-15	(29)	25.0	595.0	26.5		✓
										25.0	610.0	27.1	26.4	
										25.0	590.0	26.2		
5238	24-09-2015	Site Mix	M25	Amend		24	col.2	3-10-15	(8)	17.5	415.0	18.4		✓
										17.5	410.0	18.2	18.4	
										17.5	415.0	18.4		
5238	24-09-2015	Site Mix	M25	Amend		24	col.2	24-10-15	(29)	25.0	600.0	26.7		✓
										25.0	615.0	27.3	26.7	

5240	30-09-2015	Site Mix	M20	Amud		73	slab-1		8-10-15	(8)	140	385.0	17.1	17.2	✓
											140	385.0	17.1	17.2	
											140	390.0	17.3		
5240	30-09-2015	Site Mix	M20	Amud		73	slab-1		29-10-15	(29)	200	525.0	23.3		✓
											200	520.0	23.1	23.0	
											200	505.0	22.4		
5241	30-09-2015	Site Mix	M20	Amud		56	slab-1		8-10-15	(8)	140	350.0	15.6	15.9	✓
											140	370.0	16.4		
5241	30-09-2015	Site Mix	M20	Amud		56	slab-1		29-10-15	(29)	200	520.0	23.1	23.0	✓
											200	510.0	22.7	23.0	
											200	520.0	23.1		
5242	07-10-2015	Site Mix	M20	Amud		60	footing		15-10-15	(8)	140	385.0	17.1	17.3	✓
											140	385.0	17.1	17.3	
											140	295.0	17.6		
5242	07-10-2015	Site Mix	M20	Amud		60	footing		5-11-15	(29)	200	525.0	23.3		✓
											200	535.0	23.8	23.2	
											200	505.0	22.4		
5243	08-10-2015	Site Mix	M25	Amud		55	col-1		15-10-15	(7)	175	415.0	18.4		✓
											175	410.0	18.2	18.4	
											175	415.0	18.4		
5243	08-10-2015	Site Mix	M25	Amud		55	col-1		5-11-15	(28)	250	590.0	26.2	26.6	✓
											250	610.0	27.1	26.6	
											250	595.0	26.4		
5244	10-10-2015	Site Mix	M20	Amud		61	slab-2		17-10-15	(7)	110	355.0	17.1		✓
											140	380.0	16.9	16.8	
											140	370.0	16.4		
5244	10-10-2015	Site Mix	M20	Amud		61	slab-2		7-11-15	(28)	200	500.0	22.2		✓
											200	505.0	22.4	22.1	
											200	490.0	21.8		
5245	10-10-2015	Site Mix	M20	Amud		62	slab-2		17-10-15	(7)	140	345.0	16.3	15.4	✓
											140	355.0	16.8	15.4	
											140	340.0	15.1		
5245	10-10-2015	Site Mix	M20	Amud		62	slab-2		7-11-15	(28)	200	495.0	22.0		✓
											200	490.0	21.8	22.1	
											200	510.0	22.7		
5246	10-10-2015	Site Mix	M20	Amud		28	slab-1		17-10-15	(7)	140	350.0	16.6		✓
											140	365.0	16.9	15.7	
											140	345.0	15.3		
5246	10-10-2015	Site Mix	M20	Amud		28	slab-1		7-11-15	(28)	200	510.0	22.7		

[illegible]