

QC - Concrete Cube Testing Report.															
Company:		MRM LLP													
Project:		AGH MLG													
Report for Month:		Jun&Jul-20													
Prepared By:		QC Team													
Date:		05-09-2020													
S. No.	Date of casting	Site Mix or RMC	Specified Grade of Concrete	Supplier / Contractor	D. C. No	Block No. / Bungalow No.	Used for Slab / Columns	Slab No. or Column No.	Date of Testing	No. of days	Specified Strength	Tested Strength Kilo-newtons	Tested Strength in N per sq. mm	Avg. of three tests	Remarks
13663	04-02-2020	Site mix	M25	ashok		53	Col	2	11-2-20	7	17.5	400.0	17.8		
											17.5	395.0	17.6	17.7	
											17.5	400.0	17.8		
13663	04-02-2020	Site mix	M25	ashok		53	Col	2	4-3-20	29	25.0	575.0	25.6		
											25.0	565.0	25.1	25.3	
											25.0	570.0	25.3		
13664	07-02-2020	Site mix	M25	ashok		28	Col	2	14/2/2020	7	17.5	395.0	17.6		
											17.5	395.0	17.6	17.6	
											17.5	400.0	17.8		
13664	07-02-2020	Site mix	M25	ashok		28	Col	2	4-3-20	26	25.0	575.0	25.6		
											25.0	570.0	25.3	25.4	
											25.0	570.0	25.3		
13665	09-02-2020	Site mix	M20	ashok		54	Slab	1	18-2-20	9	14.0	325.0	14.4		
											14.0	325.0	14.4	14.4	
											14.0	320.0	14.2		
13665	09-02-2020	Site mix	M20	ashok		54	Slab	1	9-3-20	29	20.0	455.0	20.2		
											20.0	460.0	20.4	20.4	
											20.0	460.0	20.4		
13667	12-02-2020	Site mix	M20	ashok		26	Slab	2	19/02/2020	7	14.0	320.0	14.2		
											14.0	325.0	14.4	14.2	
											14.0	315.0	14.0		
13667	12-02-2020	Site mix	M20	ashok		26	Slab	2	11-3-20	28	20.0	455.0	20.2		
											20.0	455.0	20.2	20.3	
											20.0	460.0	20.4		

13668	15/2/2020	Site mix	M20	ashok		53	Slab	2	24-2-20	9	14.0	320.0	14.2		
											14.0	325.0	14.4	14.4	
											14.0	325.0	14.4		
13668	15/2/2020	Site mix	M20	ashok		53	Slab	2	14-3-20	28	20.0	460.0	20.4		
											20.0	465.0	20.7	20.5	
											20.0	460.0	20.4		
13669	16/2/2020	Site mix	M20	ashok		44	Slab	2	24-2-20	8	14.0	315.0	14.0		
											14.0	320.0	14.2	14.1	
											14.0	320.0	14.2		
13669	16/2/2020	Site mix	M20	ashok		44	Slab	2	14-3-20	27	20.0	450.0	20.0		
											20.0	460.0	20.4	20.3	
											20.0	460.0	20.4		
13670	17/2/2020	Site mix	M20	ashok		25	Slab	1	24-2-20	7	14.0	325.0	14.4		
											14.0	315.0	14.0	14.2	
											14.0	320.0	14.2		
13670	17/2/2020	Site mix	M20	ashok		25	Slab	1	15-3-20	27	20.0	455.0	20.2		
											20.0	460.0	20.4	20.4	
											20.0	460.0	20.4		
13671	18/2/2020	Site mix	M25	ashok		26	Col	3	26-2-20	8	17.5	400.0	17.8		
											17.5	395.0	17.6	17.7	
											17.5	400.0	17.8		
13671	18/2/2020	Site mix	M25	ashok		26	Col	3	18-3-20	29	25.0	565.0	25.1		
											25.0	570.0	25.3	25.3	
											25.0	570.0	25.3		
13672	19/2/2020	Site mix	M25	ashok		54	Col	2	26-2-20	7	17.5	405.0	18.0		
											17.5	405.0	18.0	17.9	
											17.5	400.0	17.8		
13672	19/2/2020	Site mix	M25	ashok		54	Col	2	18-3-20	28	25.0	575.0	25.6		
											25.0	575.0	25.6	25.5	
											25.0	570.0	25.3		
13673	21/2/2020	Site mix	M25	ashok		25	Col	2	28-2-20	7	17.5	390.0	17.3		
											17.5	395.0	17.6	17.6	
											17.5	400.0	17.8		
13673	21/2/2020	Site mix	M25	ashok		25	Col	2	20-3-20	28	25.0	565.0	25.1		
											25.0	565.0	25.1	25.2	
											25.0	570.0	25.3		
13674	22/2/2020	Site mix	M20	ashok		46	Slab	1	28-2-20	6	14.0	325.0	14.4		
											14.0	320.0	14.2	14.3	
											14.0	320.0	14.2		
13674	22/2/2020	Site mix	M20	ashok		46	Slab	1	20-3-20	27	20.0	465.0	20.7		
											20.0	460.0	20.4	20.5	

											20.0	460.0	20.4		
13675	28/2/2020	Site mix	M20	ashok		54	Slab	2	7-3-20	8	14.0	325.0	14.4		
											14.0	320.0	14.2	14.4	
											14.0	325.0	14.4		
13676	29/2/2020	Site mix	M20	ashok		26	Slab	3	7-3-20	7	14.0	320.0	14.2		
											14.0	320.0	14.2	14.1	
											14.0	315.0	14.0		
13677	05-03-2020	Site mix	M25	ashok		54	Col	3	14-3-20	9	17.5	390.0	17.3		
											17.5	395.0	17.6	17.6	
											17.5	400.0	17.8		
13678	08-03-2020	Site mix	M20	ashok		25	Slab	2	14-3-20	6	14.0	320.0	14.2		
											14.0	320.0	14.2	14.3	
											14.0	325.0	14.4		
13679	08-03-2020	Site mix	M25	ashok		46	Col	2	14-3-20	6	17.5	405.0	18.0		
											17.5	395.0	17.6	17.8	
											17.5	400.0	17.8		
13680	09-03-2020	Site mix	M20	ashok		54	Slab	3	16-3-20	7	14.0	315.0	14.0		
											14.0	320.0	14.2	14.1	
											14.0	315.0	14.0		
13681	12-03-2020	Site mix	M20	ashok		19	Slab	1	19-3-20	7	14.0	315.0	14.0		
											14.0	320.0	14.2	14.1	
											14.0	315.0	14.0		
13686	05-04-2020	Site mix	M20	ashok		27	Slab	2	5-5-20	30	20.0	465.0	20.7		
											20.0	460.0	20.4	20.4	
											20.0	455.0	20.2		
13687	08-04-2020	Site mix	M20	ashok		19	Slab	2	5-5-20	27	20.0	460.0	20.4		
											20.0	465.0	20.7	20.6	
											20.0	465.0	20.7		
13688	12-04-2020	Site mix	M25	ashok		19	Col	3	11-5-20	29	25.0	565.0	25.1		
											25.0	565.0	25.1	25.2	
											25.0	570.0	25.3		
13689	13/4/2020	Site mix	M25	ashok		27	Col	3	11-5-20	28	25.0	565.0	25.1		
											25.0	570.0	25.3	25.1	
											25.0	560.0	24.9		
13690	20/4/2020	Site mix	M20	ashok		45	Slab	1	18-5-20	28	20.0	465.0	20.7		
											20.0	460.0	20.4	20.4	
											20.0	455.0	20.2		
13691	22/4/2020	Site mix	M20	ashok		19	Slab	3	18-5-20	26	20.0	455.0	20.2		
											20.0	450.0	20.0	20.1	
											20.0	455.0	20.2		
13692	28/4/2020	Site mix	M25	ashok		46	Col	3	5-5-20	7	17.5	395.0	17.6		

											17.5	400.0	17.8	17.7	
											17.5	400.0	17.8		
13692	28/4/2020	Site mix	M25	ashok		46	Col	3	25-5-20	27	25.0	570.0	25.3		
											25.0	575.0	25.6	25.4	
											25.0	570.0	25.3		
13693	05-05-2020	Site mix	M20	ashok		46	Slab	3	13-5-20	8	14.0	315.0	14.0		
											14.0	320.0	14.2	14.1	
											14.0	320.0	14.2		
13693	05-05-2020	Site mix	M20	ashok		46	Slab	3	2-6-20	28	20.0	460.0	20.4		
											20.0	455.0	20.2	20.3	
											20.0	455.0	20.2		
13694	07-05-2020	Site mix	M25	ashok		45	Col	2	13-5-20	6	17.5	405.0	18.0		
											17.5	400.0	17.8	17.9	
											17.5	400.0	17.8		
13694	07-05-2020	Site mix	M25	ashok		45	Col	2	4-6-20	28	25.0	575.0	25.6		
											25.0	580.0	25.8	25.6	
											25.0	570.0	25.3		
13695	08-05-2020	Site mix	M20	ashok		25	Slab	3	15-5-20	7	14.0	315.0	14.0		
											14.0	325.0	14.4	14.2	
											14.0	320.0	14.2		
13695	08-05-2020	Site mix	M20	ashok		25	Slab	3	4-6-20	27	20.0	455.0	20.2		
											20.0	460.0	20.4	20.4	
											20.0	460.0	20.4		
13696	19/5/2020	Site mix	M20	ashok		28	Slab	2	28-5-20	9	14.0	320.0	14.2		
											14.0	325.0	14.4	14.3	
											14.0	320.0	14.2		
13696	19/5/2020	Site mix	M20	ashok		28	Slab	2	16-6-20	28	20.0	465.0	20.7		
											20.0	470.0	20.9	20.7	
											20.0	460.0	20.4		
13697	25/5/2020	Site mix	M20	ashok		18	Slab	1	3-6-20	9	14.0	320.0	14.2		
											14.0	325.0	14.4	14.4	
											14.0	325.0	14.4		
13697	25/5/2020	Site mix	M20	ashok		18	Slab	1	22-6-20	28	20.0	475.0	21.1		
											20.0	470.0	20.9	20.9	
											20.0	465.0	20.7		
13698	01-06-2020	Site mix	M20	ashok		27	Slab	3	9-6-20	8	14.0	320.0	14.2		
											14.0	315.0	14.0	14.1	
											14.0	315.0	14.0		
13698	01-06-2020	Site mix	M20	ashok		27	Slab	3	29-6-20	28	20.0	455.0	20.2		
											20.0	455.0	20.2	20.3	
											20.0	460.0	20.4		

13699	02-06-2020	Site mix	M25	ashok		18	Col	2	9-6-20	7	17.5	400.0	17.8		
											17.5	400.0	17.8	17.7	
											17.5	395.0	17.6		
13699	02-06-2020	Site mix	M25	ashok		18	Col	2	29-6-20	27	25.0	575.0	25.6		
											25.0	570.0	25.3	25.4	
											25.0	570.0	25.3		
13700	04-06-2020	Site mix	M25	ashok		28	Col	3	11-6-20	7	17.5	400.0	17.8		
											17.5	395.0	17.6	17.6	
											17.5	395.0	17.6		
13700	04-06-2020	Site mix	M25	ashok		28	Col	3	3-7-20	29	25.0	570.0	25.3		
											25.0	565.0	25.1	25.3	
											25.0	570.0	25.3		
13701	09-06-2020	Site mix	M20	ashok		28	Slab	3	17-6-20	8	14.0	320.0	14.2		
											14.0	315.0	14.0	14.1	
											14.0	315.0	14.0		
13701	09-06-2020	Site mix	M20	ashok		28	Slab	3	9-7-20	30	20.0	455.0	20.2		
											20.0	455.0	20.2	20.3	
											20.0	460.0	20.4		
13702	21/6/2020	Site mix	M20	ashok		45	Slab	2	27-6-20	6	14.0	320.0	14.2		
											14.0	320.0	14.2	14.3	
											14.0	325.0	14.4		
13702	21/6/2020	Site mix	M20	ashok		45	Slab	2	20-7-20	29	20.0	460.0	20.4		
											20.0	465.0	20.7	20.6	
											20.0	465.0	20.7		
13703	23-06-2020	Site mix	M25	ashok		45	Col	3	30-6-20	7	17.5	400.0	17.8		
											17.5	395.0	17.6	17.6	
											17.5	395.0	17.6		
13703	23-06-2020	Site mix	M25	ashok		45	Col	3	21-7-20	28	25.0	570.0	25.3		
											25.0	565.0	25.1	25.3	
											25.0	570.0	25.3		
13704	28-06-2020	Site mix	M20	ashok		18	Slab	2	7-7-20	9	14.0	325.0	14.4		
											14.0	320.0	14.2	14.4	
											14.0	325.0	14.4		
13704	28-06-2020	Site mix	M20	ashok		18	Slab	2	27-7-20	29	20.0	465.0	20.7		
											20.0	460.0	20.4	20.6	
											20.0	465.0	20.7		
13705	30-06-2020	Site mix	M25	ashok		18	Col	3	7-7-20	7	17.5	400.0	17.8		
											17.5	395.0	17.6	17.6	
											17.5	395.0	17.6		
13705	30-06-2020	Site mix	M25	ashok		18	Col	3	27-7-20	27	25.0	570.0	25.3		
											25.0	565.0	25.1	25.2	
											25.0	565.0	25.1		

[illegible]