

S. No.	Date of casting	Site Mix or RMC	Specified Grade of Concrete	Supplier / Contractor	D. C. No	Block No. / Bungalow No.	Used for Slab / Columns	Slab No. or Column No.	Date of Testing	No. of days	Specified Strength	Tested Strength Kilo-newtons	Tested Strength in N per sq. mm	Avg. of three tests	Remarks
20100	28-10-2020	RMC	M35	Anand		119	Footings		5-11-20	8	23.5	545.0	24.2		
											23.5	545.0	24.2	24.1	
											23.5	535.0	23.8		
20100	28-10-2020	RMC	M35	Anand		119	Footings		26-11-20	29	35.0	795.0	35.3	35.5	
											35.0	795.0	35.3		
											35.0	805.0	35.8		
20101	31-10-2020	RMC	M35	Anand		119	Footings		7-11-20	7	23.5	555.0	24.7		
											23.5	530.0	23.6	24.1	
											23.5	545.0	24.2		
20102	03-11-2020	RMC	M35	Anand		119	Footings		10-11-20	7	23.5	530.0	23.6		
											23.5	545.0	24.2	23.9	
											23.5	535.0	23.8		
20103	06-11-2020	RMC	M35	Anand		119	Footings		14-11-20	8	23.5	540.0	24.0		
											23.5	545.0	24.2	24.1	
											23.5	545.0	24.2		
20104	10-11-2020	RMC	M35	Anand		119	Footings		18-11-20	8	23.5	540.0	24.0		
											23.5	565.0	25.1	24.4	
											23.5	545.0	24.2		