QC - Concrete Cube Testing Report.

Company: MMR(LLP)

Project: GHT

Report for Month: July - Aug = 2021.

Prepared By: QC Team

Date: 01-08-2021

S. No.	Date of casting	Site Mix or RMC	Specified Grade of Concrete	Supplier / Contractor	D. C. No	Block No. / Bungalow No.	Used for Slab / Columns	Slab No. or Column No.	Date of Testing	No. of days	Specified Strength	Tested Strength Kilo-newtons	Tested Strength in N per sq. mm	Avg. of three tests	Remarks
18170	06-07-2021	Rmc	M20	Homeline		B-406-409	slab	6	4-8-21	29	20.0	485.0	21.6		
											20.0	460.0	20.4	20.7	
											20.0	450.0	20.0		
18171	13-07-2021	Site Mix	M25	Homeline		b-506-509	Columns	7	11-8-21	29	25.0	595.0	26.4		
											25.0	580.0	25.8	25.9	
											25.0	570.0	25.3		
18172	15-07-2021	Rmc	M20	Homeline		L.B.A-4,5,14,	slab	1	13-8-21	29	20.0	490.0	21.8		
											20.0	465.0	20.7	20.9	
											20.0	455.0	20.2		
18173	27-07-2021	Site Mix	M25	Homeline		A-1-5,14-1	Columns	2	4-8-21	8	17.5	420.0	18.7		
											17.5	395.0	17.6	17.8	
											17.5	385.0	17.1		
18173	27-07-2021	Site Mix	M25	Homeline		A-1-5,14-1	Columns	2	25-8-21	29	25.0	595.0	26.4		
											25.0	585.0	26.0	25.9	
											25.0	570.0	25.3		
18174	31-07-2021	Rmc	M35	Homeline		A-1-5,14-1	Columns	2	7-8-21	7	21.5	495.0	22.0		
											21.5	480.0	21.3	21.6	
											21.5	485.0	21.6		
18174	31-07-2021	Rmc	M35	Homeline		A-1-5,14-1	Columns	2	27-8-21	27	35.0	785.0	34.9		
											35.0	780.0	34.7	35.1	
											35.0	805.0	35.8		
18175	04-08-2021	Rmc	M20	Homeline		B-506-509	slab	7	13-8-21	9	14.0	310.0	13.8		
											14.0	325.0	14.4	14.1	
											14.0	320.0	14.2		
18175	04-08-2021	Rmc	M20	Homeline		B-506-509	slab	7	31-8-21	27	20.0	465.0	20.7		
											20.0	445.0	19.8	20.2	
											20.0	455.0	20.2		