QC - Concrete Cube Testing Report.

Company: MRP(LLP)

Project: NGH

Report for Month: Oct - Nov = 2021.

Prepared By: QC Team

Date: 10-12-2021

S. No.	Date of casting	Site Mix or RMC	Specified Grade of Concrete	Supplier / Contractor	D. C. No	Block No. / Bungalow No.	Used for Slab / Columns	Slab No. or Column No.	Date of Testing	No. of days	Specified Strength	Tested Strength Kilo-newtons	Tested Strength in N per sq. mm	Avg. of three tests	Remarks
22114	10-11-2021	RMC	M25	KPR Infra		A	plinth		18-11-21	8	17.5	390.0	17.3		
											17.5	390.0	17.3	17.6	
											17.5	410.0	18.2		
22114	10-11-2021	RMC	M25	KPR Infra		A	plinth		8-12-21	28	25.0	575.0	25.6		
											25.0	585.0	26.0	25.8	
											25.0	580.0	25.8		
22115	16-11-2021	RMC	M25	KPR Infra		A	plinth		25-11-21	9	17.5	395.0	17.6		
											17.5	395.0	17.6	17.8	
											17.5	410.0	18.2		
22116	25-11-2021	RMC	M30	KPR Infra		A-1,2,3.	COL	1	2-12-21	7	21.5	495.0	22.0		
											21.5	480.0	21.3	21.4	
											21.5	470.0	20.9		
22117	29-11-2021	RMC	M30	KPR Infra		A-8,9	COL	1	7-12-21	8	21.5	495.0	22.0		
											21.5	510.0	22.7	21.9	
											21.5	475.0	21.1		
22118	30-11-2021	RMC	M30	KPR Infra		A-5,6,7.	COL	1	7-12-21	7	21.5	495.0	22.0		
											21.5	490.0	21.8	21.5	
											21.5	465.0	20.7		