QC - Concrete Cube Testing Report.

Company: MRP(LLP)

Project: NGH

Report for Month: Nov - Dec = 2021.

Prepared By: QC Team

Date: 31-12-2021

S. No.	Date of casting	Site Mix or RMC	Specified Grade of Concrete	Supplier / Contractor	D. C. No	Block No. / Bungalow No.	Used for Slab / Columns	Slab No. or Column No.	Date of Testing	No. of days	Specified Strength	Tested Strength Kilo-newtons	Tested Strength in N per sq. mm	Avg. of three tests	Remarks
22115	16-11-2021	RMC	M25	KPR Infra		A	plinth		15-12-21	29	25.0	555.0	24.7		
											25.0	565.0	25.1	25.1	
											25.0	575.0	25.6		
22116	25-11-2021	RMC	M30	KPR Infra		A-1,2,3.	COL	1	23-12-21	28	30.0	695.0	30.9		
											30.0	680.0	30.2	30.3	
											30.0	670.0	29.8		
22117	29-11-2021	RMC	M30	KPR Infra		A-8,9	COL	1	28-12-21	29	30.0	700.0	31.1		
											30.0	685.0	30.4	30.5	
											30.0	675.0	30.0		
22118	30-11-2021	RMC	M30	KPR Infra		A-5,6,7.	COL	1	28-12-21	28	30.0	695.0	30.9		
											30.0	695.0	30.9	30.7	
											30.0	685.0	30.4		