QC - Concrete Cube Testing Report.

Company: MRMA(LLP)

Project: GMR

Report for Month: Oct-Nov-Dec = 20 21

Prepared By: QC Team

Date: 30-12-2021

S. No.	Date of casting	Site Mix or RMC	Specified Grade of Concrete	Supplier / Contractor	D. C. No	Block No. / Bungalow No.	Used for Slab / Columns	Slab No. or Column No.	Date of Testing	No. of days	Specified Strength	Tested Strength Kilo-newtons	Tested Strength in N per sq. mm	Avg. of three tests	Remarks
16153	03-10-2021	RMC	M20	SCPL		D-block	ab(401-40	7	11-10-21	8	14.0	325.0	14.4		
											14.0	335.0	14.9	14.6	
											14.0	325.0	14.4		
16153	03-10-2021	RMC	M20	SCPL		D-block	ab(401-40	7	1-11-21	29	20.0	450.0	20.0		
											20.0	465.0	20.7	20.7	
											20.0	480.0	21.3		
16154	05-10-2021	RMC	M20	Pointech		F-block	ab(501&50	6	11-10-21	6	14.0	310.0	13.8		
											14.0	325.0	14.4	14.1	
											14.0	320.0	14.2		
16154	05-10-2021	RMC	M20	Pointech		F-block	ab(501&50	6	1-11-21	27	20.0	445.0	19.8		
											20.0	465.0	20.7	20.2	
											20.0	455.0	20.2		
16155	08-10-2021	Site Mix	M25	SCPL		D-block	)L(501 - 50	8	17-10-21	9	17.5	410.0	18.2		
											17.5	410.0	18.2	17.9	
											17.5	390.0	17.3		
16155	08-10-2021	Site Mix	M25	SCPL		D-block	)L(501 - 50	8	6-11-21	29	25.0	575.0	25.6		
											25.0	585.0	26.0	25.9	
											25.0	585.0	26.0		
16156	20-10-2021	RMC	M20	SCPL		D-block	ab(501 -50	8	28-10-21	8	14.0	315.0	14.0		
											14.0	330.0	14.7	14.4	
											14.0	325.0	14.4		
16156	20-10-2021	RMC	M20	SCPL		D-block	ab(501 -50	8	18-11-21	29	20.0	455.0	20.2		
											20.0	465.0	20.7	20.5	
											20.0	465.0	20.7		