QC - Concrete Cube Testing Report.

Company: MRGV

Project: BRGV

Report for Month: Dec - Jan = 2022..

Prepared By: QC Team

Date: 04-02-2022

S. No.	Date of casting	Site Mix or RMC	Specified Grade of Concrete	Supplier / Contractor	D. C. No	Block No. / Bungalow No.	Used for Slab / Columns	Slab No. or Column No.	Date of Testing	No. of days	Specified Strength	Tested Strength Kilo-newtons	Tested Strength in N per sq. mm	Avg. of three tests	Remarks
21017	26-11-2021	Site Mix	M25	Homeline		A	COL	1	4-12-21	8	17.5	395.0	17.6		
											17.5	395.0	17.6	17.9	
											17.5	415.0	18.4		
21017	26-11-2021	Site Mix	M25	Homeline		A	COL	1	24-12-21	28	25.0	585.0	26.0		
											25.0	610.0	27.1	26.5	
											25.0	595.0	26.4		
21018	28-12-2021	RMC	M20	Homeline		A	Slab	6	5-1-22	8	14.0	320.0	14.2		
											14.0	315.0	14.0	14.1	
											14.0	315.0	14.0		
21018	28-12-2021	RMC	M20	Homeline		A	Slab	6	25-1-22	28	20.0	445.0	19.8		
											20.0	455.0	20.2	20.3	
											20.0	470.0	20.9		
21019	21-01-2022	RMC	M20	Homeline		A	Slab	1	29-1-22	8	14.0	325.0	14.4		
											14.0	320.0	14.2	14.4	
											14.0	325.0	14.4		
21020	27-01-2022	RMC	M25	Homeline		A	COL	2	4-2-22	8	17.5	405.0	18.0		
											17.5	395.0	17.6	17.9	
											17.5	410.0	18.2		
21021	27-01-2022	RMC	M25	Homeline		A	Footings		4-2-22	8	17.5	410.0	18.2		
											17.5	390.0	17.3	17.7	
											17.5	395.0	17.6		